



18 Stacer Street Upper Coomera QLD 4209

Mob: 0410 657 399

email: peter@slipsmart.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank Cushion – Homestead Spotted Gum

**Report Number: W1075 Date Tested: 10/08/2021** 

**Australian Standard Applied: AS4586:2013** 

**Nature and Purpose Of Tests:** 

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au



WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

## 35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank Cushion – Homestead Spotted Gum 4mm/0.55 x 228 x 1524mm\*

Standard Applied:	AS <b>4586</b> -2013	Notes:  1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface.  2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this									
Rubber Type:	Slider 96										
Fixed or unfixed surface:	Unfixed	test report.  3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.  4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.									
Cleaning type:	Nil										
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.									
Accelerated wear (if appropriate):	n/a				Fine, Dry			Date tested: 1		10/08/2021	
Slope:	n/a	Temperatur	e:	22°C			Job	Job Number: W1075			
Sample Tested			Air Temp. °C		Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification)	
Test area #1			22	4mm/0.55x228x1524mm vinyl		Nil	33				
Test area #2		22	4mm/0.55x228x1524mm vinyl		Nil	34					
Test area #3 Test area #4		22	4mm/0.5	5x228x1524mm vinyl	Nil	31	32	00	P2		
		22	4mm/0.55x228x1524mm vinyl		Nil	32					
Test area #5			22	4mm/0.5	5x228x1524mm vinyl	Nil	29				

Other observations:

ABN: 56 130 495 493

Remarks: \*Sample details supplied by Client

Signatory Brent Vournechis

Peter Vournechis

Peter Vournechis

Form:AST025B/Rev14 18 Stacer Street Upper Coomera QLD 4209 • email: peter@slipsmart.com.au Report No.W1075 Page 2 of 3



ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

