

ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209

Mob: 0410 657 399

email: peter@slipsmart.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank Cushion –Homestead Wormy Chestnut

Report Number: W1078 Date Tested: 10/08/2021

**Australian Standard Applied: AS4586:2013** 

**Nature and Purpose Of Tests:** 

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.



NATA
TECHNICAL
COMPETENCE
Accredited for compliance with
ISO/IEC 17025 - Testing
Laboratory No. 15041

## 18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

## WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

## 35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank Cushion – Homestead Wormy Chestnut 4mm/0.55 x 228 x 1524mm\*

Standard Applied:	AS <b>4586</b> -2013	Notes:  1. The areas tested below were carried out <b>on site</b> using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by wet 3 migrap language film to evaluate the frictional observatoristics of the production purface.									
Rubber Type:	Slider 96	wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface.  2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this									
Fixed or unfixed surface:	Unfixed	test report.  3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.									
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.									
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.									
Accelerated wear (if appropriate):	n/a	Environmen	Environmental Conditions: Fine, Dry				Da	Date tested: 10/08/2021			
Slope:	n/a	Temperatur	e:		22°C			Job Number:		W1078	
Sar	nple Tested		Air Temp. °C		Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification)	
Test area #1			22	4mm/0.5	55x228x1524mm vinyl	Nil	34				
Test area #2			22	4mm/0.5	55x228x1524mm vinyl	Nil	32				
Test area #3			22	4mm/0.5	55x228x1524mm vinyl	Nil	32	33	00	P2	
Test area #4			22	4mm/0.5	55x228x1524mm vinyl	Nil	34				
Test area #5			22	4mm/0.5	55x228x1524mm vinyl	Nil	31				

Other observations:

ABN: 56 130 495 493

Remarks: \*Sample details supplied by Client

Signatory		Tested By: B Vournechis
Brent Vournechis	Peter Vournechis	•

Form:AST025B/Rev14 18 Stacer Street Upper Coomera QLD 4209 • email: peter@slipsmart.com.au Report No.W1078 Page 2 of 3



ABN: 56 130 495 493



## 18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

