



ABN: 56 130 495 493 18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: <u>peter@slipsmart.com.au</u>

This report has been prepared for: *MJS Floorcoverings Pty. Ltd.* 

35 Dividend Street , Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank –Timeless Grey Report Number: W1087 Date Tested: 07/09/2021 Australian Standard Applied: AS4586:2013 Nature and Purpose Of Tests: The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.

## 



Accredited for compliance with ISO/IEC 17025 - Testing Laboratory No. 15041

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: <u>peter@slipsmart.com.au</u>

## WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: *MJS Floorcoverings Pty. Ltd.*- Kerry Krebs,

35 Dividend Street . Mansfield QLD 4122

	Test Site: L	aboratory T	ests T	ru Pla	nk – Timeless Gre	ey 2 <i>mm/</i> 0.30 x 184	l x 1219n	nm*			
Standard Applied:	AS <b>4586</b> -2013	<ul> <li>Notes:</li> <li>1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed b wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface.</li> </ul>							per followed by		
Rubber Type:	Slider 96	2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this									
Fixed or unfixed surface:	Unfixed	test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.									
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.									
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.									
Accelerated wear (if appropriate):	n/a	Environmental Conditions:						te tested:	07/09/2021		
Slope:	n/a	Temperature:			24ºC			Job Number:		W1087	
			Air Temp. °C	Floor Type		Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification	
Test area #1			24	2mm/0.30x184x1219mm vinyl		Nil	29				
Test area #2			24	2mm/0.30x184x1219mm vinyl		Nil	28				
Test area #3	est area #3		24	2mm/0.	.30x184x1219mm vinyl	Nil	29	29 <b>28</b> 26	00	P2	
Test area #4			24 <sup>2mm/0</sup> .		.30x184x1219mm vinyl	Nil	26				
Test area #5			24	2mm/0.	.30x184x1219mm vinyl	Nil	26				

Other observations:

Remarks: \*Sample details supplied by Client



Peter Vournechis



ABN: 56 130 495 493



Accredited for compliance with ISO/IEC 17025 - Testing Laboratory No. 15041

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: <u>peter@slipsmart.com.au</u>

