



ABN: 56 130 495 493

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399

email: peter@slipsmart.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank –Raw Cotton

Report Number: W1088 Date Tested: 07/09/2021

**Australian Standard Applied: AS4586:2013** 

**Nature and Purpose Of Tests:** 

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.



NATA
TECHNICAL
COMPETENCE
Accredited for compliance with
ISO/IEC 17025 - Testing
Laboratory No. 15041

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

## WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

## 35 Dividend Street, Mansfield QLD 4122

## Test Site: Laboratory Tests Tru Plank – Raw Cotton 2mm/0.30 x 184 x 1219mm\*

Standard Applied:	AS <b>4586</b> -2013	Notes:  1. The areas tested below were carried out <b>on site</b> using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface.  2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this test report.  3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.							
Rubber Type:	Slider 96								
Fixed or unfixed surface	: Unfixed								
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.							
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.							
Accelerated wear (if appropriate):	n/a		Environmental Conditions: Fine, Dry Date tested: 07/09/202				21		
Slope:	n/a	Temperature: 24°C			Job	Number: W1088			
Sa	ample Tested		Air Temp. °C	Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification)
Test area #1			24	2mm/0.30x184x1219mm vinyl	Nil	29			
Test area #2			24	2mm/0.30x184x1219mm vinyl	Nil	29			
Test area #3			24	2mm/0.30x184x1219mm vinyl	Nil	28	28	00	P2
Test area #4			24	2mm/0.30x184x1219mm vinyl	Nil	28			
Test area #5			24	2mm/0.30x184x1219mm vinyl	Nil	26			

Other observations:

ABN: 56 130 495 493

Remarks: \*Sample details supplied by Client

Signatory			Tested By: B Vournechis
	Brent Vournechis	Peter Vournechis	

Form:AST025B/Rev14 18 Stacer Street Upper Coomera QLD 4209 • email: peter@slipsmart.com.au Report No.W1088 Page 2 of 3



ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: <a href="mailto:peter@slipsmart.com.au">peter@slipsmart.com.au</a>

