



ABN: 56 130 495 493 18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: <u>peter@slipsmart.com.au</u>

This report has been prepared for: *MJS Floorcoverings Pty. Ltd.* 

35 Dividend Street , Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank –Farm Fence Report Number: W1091 Date Tested: 07/09/2021 Australian Standard Applied: AS4586:2013 Nature and Purpose Of Tests: The Nature of the Wet slip tests is as per AS4586:2013 Appendix A The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.

## 



Accredited for compliance with ISO/IEC 17025 - Testing Laboratory No. 15041

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: <u>peter@slipsmart.com.au</u>

## WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: *MJS Floorcoverings Pty. Ltd.*- Kerry Krebs,

	Test Site:	Laboratory	Tests	Tru Pl	ank – Farm Fence	2mm/0.30 x 18	4 x 1219m	m*			
Standard Applied:	AS <b>4586-</b> 2013	Notes: 1. The areas tested below were carried out <b>on site</b> using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed b wet 2 micron lapping film to evolute the frictional observatoristics of the pedestrian surface.							per followed by		
Rubber Type:	Slider 96	<ul> <li>wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface.</li> <li>SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this</li> </ul>									
Fixed or unfixed surface:	Unfixed	test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.							ove.		
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.									
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.									
Accelerated wear (if appropriate):	n/a	Environmental Conditions:						Date tested:		07/09/2021	
Slope:	n/a	e:	24°C			Job Number:		W1091			
Sample Tested Tel			Air Temp. °C		Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classificatio	
Test area #1			24	2mm/0.30x184x1219mm vinyl		Nil	35		-		
Test area #2		24	2mm/0.30x184x1219mm vinyl		Nil	31					
Test area #3			24	2mm/0	.30x184x1219mm vinyl	Nil	29	31	00	P2	
			0.4	2mm/0	.30x184x1219mm vinyl	Nil	31				
Test area #4			24		,		01				

35 Dividend Street , Mansfield QLD 4122

Other observations:

Remarks: \*Sample details supplied by Client



Peter Vournechis

Tested By: B Vournechis



ABN: 56 130 495 493



Accredited for compliance with ISO/IEC 17025 - Testing Laboratory No. 15041

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: <u>peter@slipsmart.com.au</u>

