



ABN: 56 130 495 493

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399

email: peter@slipsmart.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank –Hammer Grey

Report Number: W1092 Date Tested: 07/09/2021

Australian Standard Applied: AS4586:2013

Nature and Purpose Of Tests:

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.



ISO/IEC 17025 - Testing Laboratory No. 15041

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank – Hammer Grey 2mm/0.30 x 184 x 1219mm*

Standard Applied:	AS 4586 -2013	Notes: 1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface. 2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this							
Rubber Type:	Slider 96								
Fixed or unfixed surface	: Unfixed	test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.							
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.							
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.							
Accelerated wear (if appropriate):	n/a	Environmen	tal Con	ditions: Fine, Dry	Fine, Dry			07/09/2021	
Slope:	n/a	Temperature) :	24°C	24°C			W1092	
Sample Tested			Air Temp. °C	Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification)
Test area #1			24	2mm/0.30x184x1219mm vinyl	Nil	23		00	P1
Test area #2 Test area #3 Test area #4 Test area #5			24	2mm/0.30x184x1219mm vinyl	Nil	23	21		
			24	2mm/0.30x184x1219mm vinyl	Nil	21			
			24	2mm/0.30x184x1219mm vinyl	Nil	20			
			24	2mm/0.30x184x1219mm vinyl	Nil	19			

Other observations:

ABN: 56 130 495 493

Remarks: *Sample details supplied by Client

Tested By: B Vournechis Peter Vournechis

> Page 2 of 3 Form:AST025B/Rev14 18 Stacer Street Upper Coomera QLD 4209 • email: peter@slipsmart.com.au Report No.W1092



ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

