



ABN: 56 130 495 493 18 Stacer Street Upper Coomera QLD 4209

Mob: 0410 657 399

email: peter@slipsmart.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank – Desert Spotted Gum

**Report Number: W1093 Date Tested: 07/09/2021** 

**Australian Standard Applied: AS4586:2013** 

**Nature and Purpose Of Tests:** 

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.

Report No.W1093



NATA
TECHNICAL
COMPETENCE
Accredited for compliance with
ISO/IEC 17025 - Testing
Laboratory No. 15041

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

## 35 Dividend Street, Mansfield QLD 4122

## Test Site: Laboratory Tests Tru Plank – Desert Spotted Gum 2mm/0.30 x 184 x 1219mm\*

Standard Applied:	AS <b>4586</b> -2013	Notes:  1. The areas tested below were carried out <b>on site</b> using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by							
Rubber Type: Fixed or unfixed surface Cleaning type:	Slider 96 : Unfixed Nil	wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface.  2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this test report.  3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.  4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.							
Topography:	Lab	This report contains privileged and confidential information. The unauthorised reproduction of this report is profibiled.      While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.							
Accelerated wear (if appropriate):	n/a	Environmen				Da	te tested:	07/09/20	21
Slope:	n/a	Temperature	Temperature: 24°C				Job Number: W1093		
Sa	umple Tested		Air Temp. °C	Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification
Test area #1			24	2mm/0.30x184x1219mm vinyl	Nil	39			
Test area #2			24	2mm/0.30x184x1219mm vinyl	Nil	36			
Test area #3			24	2mm/0.30x184x1219mm vinyl	Nil	34	35	00	P3
Test area #4			24	2mm/0.30x184x1219mm vinyl	Nil	34			
Test area #5			24	2mm/0.30x184x1219mm vinyl	Nil	30			

Other observations:

ABN: 56 130 495 493

Remarks: \*Sample details supplied by Client

Signatory			Tested By: B Vournechis
	Brent Vournechis	Peter Vournechis	

Form:AST025B/Rev14 18 Stacer Street Upper Coomera QLD 4209 • email: peter@slipsmart.com.au Report No.W1093 Page 2 of 3



ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

