



ABN: 56 130 495 493

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399

email: <u>peter@slipsmart.com.au</u>

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank – Wood Smoke

Report Number: W1094 Date Tested: 07/09/2021

**Australian Standard Applied: AS4586:2013** 

**Nature and Purpose Of Tests:** 

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.

Report No.W1094



Lab

n/a

n/a

ISO/IEC 17025 - Testing Laboratory No. 15041

**P2** 

Job Number: W1094

33

00

31

35

30

## 18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

## WET Slip Resistance Test Report for Pedestrian Surfaces

Temperature:

24

24

24

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

## 35 Dividend Street, Mansfield QLD 4122

## Test Site: Laboratory Tests Tru Plank – Wood Smoke 2mm/0.30 x 184 x 1219mm\* Notes: Standard Applied: AS **4586**-2013 1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by wet 3 micron lanning film to evaluate the frictional characteristics of the nedestrian surface

24°C

Rubber Type:	Slider 96	2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this	
Fixed or unfixed surface:	Unfixed	test report.  3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.	
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.	

4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited. 5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors

Nil

Nil

or omissions or that it will be suitable for the client's purposes. Date tested: 07/09/2021 **Environmental Conditions:** Fine, Dry

Air **British** Slip Slope Equivalent Sample Tested Temp. Floor Type Pendulum Resistance Correction AS4586-2013 Coating Classification Number Value °C 2mm/0.30x184x1219mm vinyl Nil Test area #1 24 36 Nil 2mm/0.30x184x1219mm vinyl Test area #2 24 34 2mm/0.30x184x1219mm vinyl Nil

2mm/0.30x184x1219mm vinyl

2mm/0.30x184x1219mm vinyl

Other observations:

Test area #3

Test area #4

Test area #5

ABN: 56 130 495 493

Topography:

Slope:

Accelerated wear (if appropriate):

Remarks: \*Sample details supplied by Client

Signatory			Tested By: B Vournechis
	ournechis	Peter Vournechis	

Form: AST025B/Rev14 18 Stacer Street Upper Coomera QLD 4209 • email: peter@slipsmart.com.au Report No.W1094 Page 2 of 3



ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

