



ABN: 56 130 495 493

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399

email: peter@slipsmart.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank - Cappuccino

Report Number: W1097 Date Tested: 07/09/2021

Australian Standard Applied: AS4586:2013

Nature and Purpose Of Tests:

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.



ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank – Cappuccino 2mm/0.30 x 184 x 1219mm*

Standard Applied:	AS 4586- 2013	Notes: 1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface.								
Rubber Type:	Slider 96	2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this								
Fixed or unfixed surface:	Unfixed	test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.								
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.								
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.								
Accelerated wear (if appropriate):	n/a	Environmental Conditions: Fine, Dry				Da	Date tested: 07/09/2021		21	
Slope:	n/a	Temperature:	Temperature: 24°C			Job	Job Number: W		W1097	
San	nple Tested	A Ter °(np.	Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification)	
Test area #1		2	4 2mm/0).30x184x1219mm vinyl	Nil	37				
Test area #2		2	4 2mm/0	0.30x184x1219mm vinyl	Nil	35				
Test area #3		2	4 2mm/0	0.30x184x1219mm vinyl	Nil	35	35	00	Р3	
Test area #4		2	4 2mm/0	0.30x184x1219mm vinyl	Nil	36				
Test area #5		2	4 2mm/0	0.30x184x1219mm vinyl	Nil	34				

Other observations:

Remarks: *Sample details supplied by Client

Signator			Tested By: B Vournechis
	Brent Vournechis	Peter Vournechis	



ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

