



ABN: 56 130 495 493

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399

email: peter@slipsmart.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank – Outback Spotted Gum

Report Number: W1098 Date Tested: 07/09/2021

Australian Standard Applied: AS4586:2013

Nature and Purpose Of Tests:

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.

Report No.W1098



NATA
TECHNICAL
COMPETENCE
Accredited for compliance with
ISO/IEC 17025 - Testing
Laboratory No. 15041

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank – Outback Spotted Gum 2mm/0.30 x 184 x 1219mm*

Standard Applied:	AS 4586 -2013	Notes: 1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by									
Rubber Type:	Slider 96	 wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface. 2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above. 4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited. 									
Fixed or unfixed surface:	Unfixed										
Cleaning type:	Nil										
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.									
Accelerated wear (if appropriate):	n/a	Environmental Conditions:			Fine, Dry			Date tested:		07/09/2021	
Slope:	n/a	Temperature:			24°C			Job Number: \		W1098	
Sar	mple Tested		Air Temp. °C		Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification)	
Test area #1			24	2mm/0.3	0x184x1219mm vinyl	Nil	35				
Test area #2		24	2mm/0.3	mm/0.30x184x1219mm vinyl Nil		34					
Test area #3	Test area #3 Test area #4		24	2mm/0.3	0x184x1219mm vinyl	Nil	36	35	00	Р3	
Test area #4			24	2mm/0.3	0x184x1219mm vinyl	Nil	35				
Test area #5			24	2mm/0.3	0x184x1219mm vinyl	Nil	35				

Other observations:

ABN: 56 130 495 493

Remarks: *Sample details supplied by Client

Signatory		Tested By: B Vournechis
Brent Vournechis	Peter Vournechis	

Form:AST025B/Rev14 18 Stacer Street Upper Coomera QLD 4209 • email: peter@slipsmart.com.au Report No.W1098 Page 2 of 3



ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

