



ABN: 56 130 495 493

18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399

email: peter@slipsmart.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank – Coastal Spotted Gum

Report Number: W1100 Date Tested: 07/09/2021

Australian Standard Applied: AS4586:2013

Nature and Purpose Of Tests:

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.



NATA
TECHNICAL
COMPETENCE
Accredited for compliance with
ISO/IEC 17025 - Testing
Laboratory No. 15041

18 Stacer Street Upper Coomera QLD 4209 Mobi 0410 657 399 email: peter@slipsmart.com.au

WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank – Coastal Spotted Gum 2mm/0.30 x 184 x 1219mm*

Standard Applied:	AS 4586 -2013	Notes: 1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface. 2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this									
Rubber Type:	Slider 96										
Fixed or unfixed surface:	Unfixed	test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.									
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited. 5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.									
Topography:	Lab										
Accelerated wear (if appropriate):	n/a	Environmental Conditions:			Fine, Dry			Date tested: 0		07/09/2021	
Slope:	n/a	Temperature:			24°C			Job Number: V		W1100	
Sample Tested			Air Temp. °C		Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification)	
Test area #1			24	2mm/0.3	0x184x1219mm vinyl	Nil	29				
Test area #2			24	2mm/0.3	2mm/0.30x184x1219mm vinyl Nil		26				
Test area #3	Test area #3 Test area #4		24	2mm/0.3	0x184x1219mm vinyl	Nil	25	26	00	P2	
Test area #4			24	2mm/0.3	0x184x1219mm vinyl	Nil	28				
Test area #5			24	2mm/0.3	0x184x1219mm vinyl	Nil	24				

Other observations:

ABN: 56 130 495 493

Remarks: *Sample details supplied by Client

Signatory Brent Vournechis

Peter Vournechis

Peter Vournechis



ABN: 56 130 495 493



18 Stacer Street Upper Coomera QLD 4209 Mob: 0410 657 399 email: peter@slipsmart.com.au

