



ABN: 60 341 526 043

18 Stacer Street Upper Coomera, QLD 4209

Mob: 0410 657 399

email: info@slipsmartaustralia.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank Cushion – Homestead Flood Gum

Report Number: W1129
Date Tested: 02/02/2022

Australian Standard Applied: AS4586:2013

Nature and Purpose Of Tests:

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.





18 Stacer Street Upper Coomera QLD 4209

Mob: 0410 657 399

email: info@slipsmartaustralia.com.au

WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

25 Dividend Street Manefield OLD 4122

Standard Applied:	AS 4586 -2013	y Tests Tru Plank Cushion – Homestead Flood Gum 4mm/0.55 x 228 x 1524mm* Notes: 1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by								
Rubber Type:	Slider 96	 wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this 								
Fixed or unfixed surface:	Unfixed	test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.								
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.								
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.								
Accelerated wear (if appropriate):	n/a	Environment						22		
Slope:	n/a	Temperature) :	25°C			Job	Job Number: W1129		
Sai	mple Tested		Air Temp. °C	Floo	r Туре	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalen AS4586-201 Classificatio
Test area #1			25	4mm/0.55x228	8x1524mm vinyl	Nil	33			
Test area #2			25	4mm/0.55x228	8x1524mm vinyl	Nil	30			
Test area #3		25	4mm/0.55x228x1524mm vinyl		Nil	29	30	00	P2	
Test area #3			25	4mm/0.55x228	8x1524mm vinyl	Nil	31			
Test area #4			25							

Remarks: *Sample details supplied by Client

Signatory Rrent Vournechis	Peter Vournechis	Tested By: B Vournechis
Brent Vournechis	Peter Vournechis	



18 Stacer Street Upper Coomera QLD 4209

email: info@slipsmartaustralia.com.au

Mob: 0410 657 399

