



ABN: 60 341 526 043 18 Stacer Street Upper Coomera, QLD 4209 Mob: 0410 657 399 email: <u>info@slipsmartaustralia.com.au</u>

This report has been prepared for: *MJS Floorcoverings Pty. Ltd.*

35 Dividend Street , Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank Cushion – Homestead Ironbark Report Number: W1131 Date Tested: 02/02/2022 Australian Standard Applied: AS4586:2013 Nature and Purpose Of Tests: The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.





18 Stacer Street Upper Coomera QLD 4209 email: <u>info@slipsmartaustralia.com.au</u>

Mob: 0410 657 399

WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: *MJS Floorcoverings Pty. Ltd.*- Kerry Krebs,

35 Dividend Street , Mansfield QLD 4122

Те	st Site: Laborato	ry Tests Tru	ı Plan	k Cusl	hion – Homestead	l Ironbark 4mm/0.	55 x 228	x 1524m	m *	
Standard Applied:	AS 4586 -2013	 Notes: 1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface. 						per followed by		
Rubber Type:	Slider 96	 2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above. 4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited. 5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. 								
Fixed or unfixed surface	: Unfixed									
Cleaning type:	Nil									
Topography:	Lab									
Accelerated wear (if appropriate):	n/a	Environmental Conditions: Overcast					Da	Date tested: 02/02/2022		
Slope:	n/a	Temperature:			25°C		Job Number:		W1131	
Sample Tested					Floor Type	Coating	British Pendulum Number	Slip Resistance Value	Slope Correction Value	Equivalent AS4586-2013 Classification
Test area #1			25	4mm/0.55x228x1524mm vinyl 4mm/0.55x228x1524mm vinyl 4mm/0.55x228x1524mm vinyl		Nil	40	39	00	Р3
Test area #2 Test area #3 Test area #4 Test area #5			25			Nil	40			
			25			Nil	41			
			25	4mm/0	nm/0.55x228x1524mm vinyl Nil 36					
			25	4mm/0	.55x228x1524mm vinyl	Nil	36			

Other observations:

Remarks: *Sample details supplied by Client



Peter Vournechis

Tested By: B Vournechis





18 Stacer Street Upper Coomera QLD 4209 email: <u>info@slipsmartaustralia.com.au</u> Mob: 0410 657 399

