



ABN: 60 341 526 043

18 Stacer Street Upper Coomera, QLD 4209

Mob: 0410 657 399

email: info@slipsmartaustralia.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Tru Plank Cushion – Valley Oak

Report Number: W1134 Date Tested: 02/02/2022

Australian Standard Applied: AS4586:2013

Nature and Purpose Of Tests:

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.





18 Stacer Street Upper Coomera QLD 4209 email: info@slipsmartaustralia.com.au

Mob: 0410 657 399

WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

35 Dividend Street Mansfield QLD 4122

Standard Applied:	AS 4586 -2013	Notes: 1. The areas tested below were carried out on site using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed by wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface.								
Rubber Type:	Slider 96	2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this								
Fixed or unfixed surface:	Unfixed	test report. 3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above. 4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.								
Cleaning type:	Nil									
Topography:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.								
Accelerated wear (if appropriate):	n/a	Environmen	Environmental Conditions: Overcast				Da	Date tested: 02/02/2022		
Slope:	n/a	Temperature	Temperature: 25°C				Job	Job Number: W1134		
San	Sample Tested		Temp. °C	Floor Type		•	Number		Slope Correction Value	Equivalent AS4586-2013 Classification
Test area #1			25	4mm/0.5	5x228x1524mm vinyl	Nil	38			
Test area #2			25	4mm/0.5	5x228x1524mm vinyl	Nil	36			
Test area #3		25	4mm/0.55x228x1524mm vinyl		Nil	34	35	00	Р3	
Test area #4		25	4mm/0.55x228x1524mm vinyl		Nil	33				
Test area #4		Test area #5				Nil				

Signatory	Data Variancialis	Tested By: B Vournechis
Brent Vournechis	Peter Vournechis	

Report No.W1134



18 Stacer Street Upper Coomera QLD 4209

email: info@slipsmartaustralia.com.au

Mob: 0410 657 399

