



ABN: 60 341 526 043

18 Stacer Street Upper Coomera, QLD 4209

Mob: 0410 657 399

email: info@slipsmartaustralia.com.au

This report has been prepared for: MJS Floorcoverings Pty. Ltd.

35 Dividend Street, Mansfield QLD 4122

Test Site: Laboratory Tests Sample Tile – Polished Concrete Pumice

Report Number: W1136 Date Tested: 02/02/2022

**Australian Standard Applied: AS4586:2013** 

**Nature and Purpose Of Tests:** 

The Nature of the Wet slip tests is as per AS4586:2013 Appendix A

The purpose of the Wet slip test is to ascertain an SRV for the surfaces requested.





18 Stacer Street Upper Coomera QLD 4209

email: <u>info@slipsmartaustralia.com.au</u>
Mob: 0410 657 399

## WET Slip Resistance Test Report for Pedestrian Surfaces

This report has been prepared for: MJS Floorcoverings Pty. Ltd.- Kerry Krebs,

Standard Applied:	AS <b>4586</b> -2013		Notes:  1. The areas tested below were carried out <b>on site</b> using the Wessex Pendulum friction tester ID: SK1271, conditioned with grade P400 paper followed be wet 3 micron lapping film, to evaluate the frictional characteristics of the pedestrian surface.					per followed by			
Rubber Type:	Slider 96	2. SlipSmart Pty Ltd assumes no responsibility or civil liability for any actions whatsoever that may arise as a result of the tests and the publication and issue of this									
ixed or unfixed surface:	Unfixed	test report.  3. Slip test results always remain the property of SlipSmart Pty Ltd. This test report is intended for viewing solely for the named recipient identified above.									
Cleaning type:	Nil	4. This report contains privileged and confidential information. The unauthorised reproduction of this report is prohibited.									
Гороgraphy:	Lab	5. While SlipSmart Pty Ltd takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes.									
ccelerated wear (if appropriate):	n/a	Environmen	Environmental Conditions: Ove				Da	Date tested:		02/02/2022	
Slope:	n/a	Temperature	e:	25°C			Job	Job Number: W1136			
Sample Tested			Air Temp. °C	4mm/0.4	Floor Type  55x228x1524mm vinyl	Coating Nil	Number	Slip Resistance Value	Slope Correction Value	Equivaler AS4586-20 Classificati	
Test area #1			25		,		42				
Test area #2		25	4mm/0.55x228x1524mm vinyl		Nil	46		00	P3		
Test area #3		25	4mm/0.55x228x1524mm vinyl		Nil	42	43				
Test area #4		25	4mm/0.55x228x1524mm vinyl		Nil	42					
Test area #5			25	4mm/0.55x228x1524mm vinyl Nil		Nil	44				

Signatory Brent Vournechis	Peter Vournechis	Tested By: B Vournechis
DICHE VOULICHIS	reter vountechis	



## 18 Stacer Street Upper Coomera QLD 4209 email: <a href="mailto:info@slipsmartaustralia.com.au">info@slipsmartaustralia.com.au</a>

Mob: 0410 657 399

