



Accredited for compliance with ISO/IEC 17025 – Testing  
NATA is a signatory to the ILAC Mutual Recognition Arrangement for the mutual recognition of the equivalence of testing, medical testing, calibration and inspection reports

## OIL-WET INCLINING PLATFORM SLIP RESISTANCE TEST

### Somplan 350 sheet vinyl

**Prepared for:** Tarkett Australia Pty Ltd  
Paul Roberts  
Suite 1, Level 3, 3 Columbia Court  
BALKHAM HILLS NSW 2153

**Specimen Description:** Somplan 350 sheet vinyl, 500x1000 mm.

**No. of Specimens:** 1 off

**Surface Structure:** Smooth

**Specimen Preparation:** Washed with water and pH neutral detergent, rinsed then dried.

**Specimen Configuration:** Fixed

**Test Direction:** Test direction not applicable.

**Joint Type & Width:** N/A

**Air Temperature:** 22°C

**Test Standard:** AS 4586:2013 Slip resistance classification of new pedestrian surface materials, Appendix D - Oil Wet Inclining Platform Test

**Test Shoe:** Leipzig V73-SP

**Test Location:** ATTAR, Unit 1, 64 Bridge Road, Keysborough.

**Test Date:** 22 December 2020

**Test Personnel:** Dale Siegle and Marcus Braché

<b>Displacement Space</b> (rounded to the nearest 0.5cm <sup>3</sup> /dm <sup>2</sup> ):	Not tested
<b>Displacement Space Assessment Group</b> (Appendix E, AS 4586 - 2013):	Not tested
<b>Corrected mean overall acceptance angle (<math>\alpha_{ave}</math>)</b> (rounded down to the nearest degree):	10°
<b>Classification:</b>	R10

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance procedures and wear on their slip resistance be checked.




Marcus Braché  
Senior Engineering Technician  
Approved Signatory

Reviewed By:



Dale Siegle  
Compliance and Test Technician  
Approved Signatory



**Figure 1:** Somplan 350 sheet vinyl

**CLASSIFICATION CRITERIA – AS 4586 - 2013**  
**Oil Wet Inclining Platform Test – Appendix D**

**Compliance**

**TABLE 5: CLASSIFICATION OF PEDESTRIAN SURFACE MATERIALS ACCORDING TO THE OIL-WET INCLINING PLATFORM TEST**

<b>Classification</b>	<b>Angle, degrees</b>
No Classification	<6
R9	≥6 <10
R10	≥10 <19
R11	≥19 <27
R12	≥27 <35
R13	≥35